

# *Data Sheet*

## Peri - Beton - Konen

Compression Strength on cube 100x100x100 mm	55 N / mm <sup>2</sup>
Dimensional Accuracy	+/-1 mm
Water Penetration Depth	< 8 mm
Exposure class, DIN 1045-L, 2001	all exposure classes are fulfilled
Ingredients with German / European Approval	Portland cement CEM I 42,5 N
	Silica Fume
	Glas Fibres 6mm
	Calcium Carbonate Powder
	Plasticizer
	Quartz Sand
asbestfrei - asbestos free - sans amiante	

Rothenkirchen, May 2016